

Document type	Technical Data Sheet
Name	MARMORINO FINE
Description	Natural, lime-based material for decorative finishes on interior wall surfaces. Naturally anti-mould and breathable. This Venetian plaster has fine grain size, and therefore is very glossy, rich in trowel movements, and gentle chiaroscuro that convey a pleasant sense of depth.
Composition	Aged, slaked lime and selected marble powders.
Grain size	Marble: 60 microns. Lime: 100 microns.
Appearance	Paste
Colour	White, it can be tinted in any colour with lime-compatible colourants
Packaging	24 kg net polyethylene containers 16 kg net polyethylene containers 8 kg net polyethylene containers
Application	By hand, with a steel trowel
Type of Surface	Interior walls. <u>New Wall Surface</u> Plaster: no priming necessary Gypsum / Plasterboard / Medium Density: one coat of DEKO PRIMER <u>Old Wall Surface</u> Plaster: one coat of DEKO PRIMER Fast drying / Limewash: brush down and apply one coat of DEKO PRIMER Polished Lime: Abrade, brush down and apply one coat of DEKO PRIMER Washable Paint: one coat of DEKO PRIMER
Dilution	Ready to use
Consumption	850 g/m ² after three coats
Drying	3 hours at 20°C / 68°F to the touch 48 hours at 20°C / 68°F below the surface 180 days stable
Application temperatures	min 5 max 30°C – R.U. < 85% ca
Coat Thickness	0.8 – 1.2 mm for a total of 3 coats
VOC Classification	EU Directive 2004/42/CE: EU limit value for this product (cat A/I – water-based decorative effect coating): 200 g/l (2010). This product contains less than 1 g/l of VOC.
Specific Weight	1.4 ± 0.2 (kg/l)
pH after 30 days	12.5 ± 0.50
Vapour Permeability	SD ~ 0,04 m (DIN 52 615)
Flammability	European Class of Reaction to Fire A1: non-combustible, no contribution to fire
Mould Resistance	ASTM D 3274 – “Standard Test Method to evaluate the degree of surface disfigurement of paint by microbial, fungal and algae growth. Result: Front Panel 10/10/10 Back Panel 10/10/10 = no growth

Scrub Test Resistance	ASTM D 2486-06 method A = was used: scrubbing fine sand + metallic brush for 10,000 cycles
Impact Test	UNI EN ISO 6272-2-2006. 1 kg doming punch was dropped from different heights and only at the height of 8 cm., it left a 5.5 mm. dent in the surface and a tiny crack appeared around its circumference.
Pencil Hardness	ASTM D3363- Pencil hardness 5H
Shore Hardness	Norm ASTM 2240 average
Adhesion	Norm UNI EN 13892-8 2004 average value = 2,0
Shelf life	36 months when stored according to the recommended guidelines
Storage	In original sealed packaging between 5° - 35°C in a dry, dark environment
Safety Norms	Irritating. / Risk of serious damage to eyes. / Irritating to the skin. / Keep out of children. / Avoid contact with eyes. / In case of contact with eyes, clean immediately with water without rubbing them, and consult a doctor. / Wear suitable gloves and eyes / face protection. / In case of ingestion of the products, consult immediately a doctor showing him the can or the label of the product. Danger labelling under directives 67/548/EEC and 1999/45/EC and following amendments and adjustments. The product must be transported, used and stored according to current standards of hygiene and safety.
Disposal	Product must be disposed of according to norms and regulations in force. Containers must be sent for recycling. Follow directions on the packaging
Application Instructions	<p>WARNINGS</p> <p>Water on the surface of the material in the bucket is normal and should be removed before use or addition of colourants. All lime-based products lose their viscosity when mixed and need a period of 6/12 hours after mixing to regain their density. This product is dense, and ready for use; thus it may be necessary to use an appropriate drill attachment to stir for a few minutes to reduce viscosity. Choose the colour and add the toner additive to the container and continue mixing until a homogeneous shade is obtained. Let the product rest for about 5 hours before you begin to use it.</p> <p>We recommend using materials from the same production batch for the same project. If you must use different batches, we suggest mixing their material together to avoid any slight variations in shading.</p> <p>To ensure proper usage, dilution, and application of the products mentioned in these pages, please consult the corresponding technical data sheets.</p> <p>When preparing the surface and applying the materials, we advise using appropriate tools and personal protective equipment (PPE).</p> <p>During application and for the following 72 hours, protect the surfaces from sudden temperature change, direct sun light and water. Don't apply in temperatures below 8°C or above 35°. During application make sure that the work area isn't too damp to avoid problems with application times.</p> <p>Remember to have a strong light parallel to the wall and situated on only one of the two sides of the wall you are working on (usually on the same side as other sources of light such as windows). In this way the shadow of the trowel allows you to see the actual state of the finish. Every so often, during the second and third coat, the light</p>

should be moved so that the wall doesn't dry out too much in one spot from the heat of the lamp.

APPLICATION

Protection of the work area: Masking tape and protective material over the baseboards and around windows and doors.

MARMORINO FINE can be applied to a plaster (rough or smooth, new or not insulated). Already painted surfaces require a thorough brushing down to remove dust and uneven parts. Where necessary, use a brush or roller to apply a coat of DEKO PRIMER. Apply at least three coats of MARMORINO FINE with a steel trowel.

1) First coat of MARMORINO FINE: use ca. 400 g/sqm. This coat is applied directly to the plaster, taking care to apply it evenly so as to smooth out any imperfections. This coat must not be shiny, or you will face problems of low adhesion or detached product when applying the final coat.

2) Second coat of MARMORINO FINE: Begin applying only after the first coat is dry. Use ca. 320 g/sqm, taking care that the surface is as smooth and ridges-free as possible, but DO NOT POLISH as this will cause problems for the adhesion of the final finish coat.

3) Third coat of MARMORINO FINE: Use ca. 120 g/sqm. Apply before the second coat is completely dry, that is WET INTO WET, so that the granules of marble penetrate the previously applied coat. After this, proceed with the final smoothing and polishing. For greater polish, go over the surface repeatedly with a trowel. This is the final coat and will need to be gone over a number of times with the trowel so as to polish the surface. The wall in turn becomes shiny by the pressure applied to the blade of the trowel on the wall.

Finish Protection (optional)

BEESWAX / MINERAL WAX / MARSEILLE SOAP / HYDROCALCE

A protective treatment is optional in most circumstances. It is however necessary in bathroom walls, kitchen, and splashback walls.

After a minimum of 48 hours, at least one coat of the following can be applied:

A) MARSEILLE SOAP protective coating with a steel trowel. Use ca. 30-50 g/sqm. After 48 hours, go over the surface with a cloth to remove the coat of surface powder produced by unabsorbed soap.

B) A coat of BEESWAX applied with a sponge. Use ca. 30-50 g/sqm. After a little while, before it dries, rub vigorously with a woollen or soft cloth to obtain an even polish.

C) A coat of MINERAL WAX applied with a sponge. Use ca. 30-50 g/sqm. After a little while, before it dries, rub vigorously with a woollen or soft cloth to obtain an even polish.

Maintenance

No special work is required in maintenance, just remove the dust periodically and re-wax it after 5 or 6 years. Protect the coating from any contact with liquid either rain or continuous water flowing down the wall. If any liquid such as coffee is spilled on the surface, clean immediately.



Tools	SI TROWEL/ BIANCO, CORNER TROWEL, SCRAPERS, NON-WOVEN FABRIC Clean with water immediately after use
Decorative complements (optional)	TERRACOTTA FINE / MILLED MARBLE / MICA / GLITTER / EBANO POWDER METALLIC BEESWAX / PERLA WAX

We have drawn up the material presented above to the best of our technical and experiential knowledge. Nevertheless, our suggestions and recommendations are not guaranteed. All responsibility for the obtained results lies solely with the method and conditions adopted for the application of the product. Such indications constitute valid support for verifying the product's suitability for the specific case. We reserve the right to make modifications to the present information without previous warning.